



SEALWISE®
NEDERLAND

Chemical resistance chart

Long term exposure, 24 hours+

All of this information is based on 24 hours+ exposed to three specific temperature ranges

		RESISTANT	PARTIAL RESISTANCE	NO RESISTANCE
Waste Gases	20°	✓		
	40°	✓		
	60°	✓		
Waste gases with oxidising effect	20°		✓	
	40°			✓
	60°			✓
Inorganic acids	20°	✓		
	40°	✓		
	60°			
Inorganic acids, with oxidising effect	20°	✓		
	40°	✓		
	60°			
Amides, nitrites	20°	✓		
	40°			✓
	60°			✓
Mineral oils, fuels, nonaromatic	20°	✓		
	40°		✓	
	60°			
Organic acids	20°	✓		
	40°	✓		
	60°			
Alkalis	20°	✓		
	40°	✓		
	60°	✓		
Halogens	20°		✓	
	40°			✓
	60°			✓
Salts	20°	✓		
	40°	✓		
	60°	✓		
Salts, with oxidising effects	20°	✓		
	40°	✓		
	60°			
Aldehydes	20°	✓		
	40°			✓
	60°			✓
Aliphatic hydrocarbons, saturated	20°	✓		
	40°	✓		
	60°			
Alcohols, glycols	20°		✓	
	40°		✓	
	60°		✓	

*Please note: Chart highlights group chemical testing rather than individual Chemicals, for specific information please speak to a Sealwise member of staff.



SEALWISE®
NEDERLAND

Industrieweg 93
5145 PD Waalwijk
Postbus 18
5140 AA Waalwijk
T +31 (0)416 700260
www.sealwise.nl
info@sealwise.nl